

Product - Data - Sheet

ESBAND Type	SKO 48.24		data-sheet no.
Material	Linen		40-4824.01
Tape surface	plain		
Tape thickness ⁽¹⁾	0,52 mm		
Lateral tape flexibility	very high		
Temperature-resistance	up to 120 °C		
Wear resistance	high		
Breaking strength	1100 N/cm	-8,0 %	
Elongation of endless tape at 150 N/cm pre-tension	0,80 %	± 0,2 %	
coefficient of friction ⁽²⁾ to paper to garniture	0,40 µ	± 0,1 µ	
	0,16 µ	± 0,1 µ	
Tolerances length width thickness wobble	+ 1,0 % / - 0,0 % + 0,0 mm / - 0,5 mm + 0,05 mm / - 0,02 mm max. 0,8 mm (max. 1,2 mm for tape length exceeding 4000 mm)		
Recommended for Cigarette Production	PROTOS1-8 PROTOS 70, 80, 90, 90E PROTOS 2, 2-2	GD 1-2-1 PASSIM Decouflé 3D	
⁽¹⁾ - At measured pressure of 0,7 N/cm ² ⁽²⁾ - Average values determined to SCHLATTERER norm MSN 98.105 All data in this data-sheet correspond to the lates state of the art. Modifications are possible without prior notice. The values stated are for information only; they do not guarantee a specific property.			Edition: 05.01.2011 Copyright ESBAND